

APPENDIX G

Riprap Material

Wastron

11-12-2001

This is to certify that the Class 7(Rip Rap) material produced by Boxley Aggregates, meets all West Virginia Department of Highways specifications under section 704.6.2

Shotrock is deposited in the feeder, which then transports material to the jaw. The jaw then sizes the Class 7, (Rip Rap) material, then the material travels up a beltline and separated by a deflecting plate. The material which comes off the deflecting plate is stockpiled as Class 7 material (Rip Rap).

No screens are used in the process of making Class 7. (Rip Rap).

This material meets 90-100% passing the 8" screen, 0-5% passing the 2" screen, and with intermediate sizes between 6" and 4" represented.

This material is produced at our Beckley (Sand Branch Rd.) WV location.

Boxley Aggregates

FORM 17

1332289

LABORATORY NUMBER

1 1148

FORM & MATERIAL CODES

09/24/01

DATE REPORTED

WEST VIRGINIA DEPARTMENT OF HIGHWAYS
TESTING LABORATORIES
REPORT ON SAMPLE

ROAD & ROUTE INFORMATION

COUNTY INA

DISTRICT

INA

PROJECT

INA

STATION

0+ 0 TO 0+ 0

OFFSET

0000.0 FT FROM

TYPE OF SAMPLE

AGG SANDSTONE #57

FIELD SAMPLE NUMBER

M0-1666

ITEM NUMBER

BRIDGE NUMBER

QUANTITY REPRESENTED BY THIS SAMPLE

3000.00 TN

TEST REQUIRED - (IDENTIFY GOVERNING SPECIFICATIONS)

703

DATE SAMPLED

08/07/01

SAMPLED BY

M CLYBURN

ELEVATION

0.0 TO 0.0

SOURCE

BOXLEY AGG. (BECKLEY PLANT)
BECKLEY W VA
8219A

OTHER IDENTIFICATION

LA	30
SOUNDNESS	1.0
DEL SHALE	0.3
COAL LT WT	0.0
DEL T & E	0.0
DEL FRIABL	0.00

MEETS SPECIFICATION REQUIREMENTS

RECEIVED

OCT 02 2001

DISTRICT 10
MATERIALS LAB

BARNEY C. STINNETT

SUBMITTED BY: ENGINEER AND MATERIALS OF TESTS